


GLOBALFLOR ULTRAFLEX

RUBBER-PLASTIC HOMOGENEOUS SHEET



TECHNICAL DATA		TEST STANDARD REQUIREMENT	ULTRAFLEX
Type of floor covering			Compact Rubber-plastic Flooring Sheet
Total thickness	EN 428		2.0mm
Roll width	EN 426		2m
Roll length	EN 426		20m
Weight	EN 430		3000g/m ²
Classification	EN 649		34/43
Fire rating	GB/T11785-2005		Bfl-s1
Smoke density	GB/T11785-2005	≤750% min	Pass
Toxic	GB/T20285-2006	t0 achieve ZA	Pass
Residual indentation	HG/T3747.1-2011 6.8	0.25mm	Pass
Dimension stability	HG/T3747.1-2011 6.3	±0.4%	Pass
Slip resistance	DIN 51130		R10
Flexibility	HG/T3747.1-2011 6.6		No crack
Anti cigarette	HG/T3747.1-2011 6.5	≥Level 3	Level 3
Color fastness	HG/T8427-2019	≥Level 3	Level 4
Environment Test			
Soluble lead	GB18586-2001.5.4	≤20mg/m ²	Pass
Soluble cadmium	GB18586-2001.5.4	≤20mg/m ²	Pass
VOC	GB18586-2001.5.5	≤50g/m ²	Pass
Formaldehyde	GB185B3-2008	≤0.5g/kg	Pass
Stain Resistance Test			
Diluted hydrochloric acid	ISO26987:2008	2h	No effect
84 Disinfectant	ISO26987:2008	2h	No effect
Sodium hydroxide (25%)	ISO26987:2008	2h	No effect
Hydrogen peroxide (30%)	ISO26987:2008	2h	No effect
Blackening (shoe)	ISO26987:2008	2h	No effect
Alcohol	ISO26987:2008	2h	No effect
Structure	UV coating, Compact rubber-plastic homogeneous layer (special hammered surface emboss)		
Installation method	Full spread adhesive		
Seaming method	Seamless seal with double-component adhesive		
Applications	Interior commercial areas with high traffic and light industrial areas		
Package and loading	16rolls per pallet, 10 pallets per 20ft GP, in total 6400sq.m.. Or 8000sq.m. without pallet		

Please note: Globalflor has a policy of continuous product and product data improvement, it reserves the right to change design and specifications without notice. For the latest Technical Data Sheet, please kindly check www.bomeiflor.com